

Laboratory data summary

Wood pellets | Independent sample analysis | Commercial reference sheet

LABORATORY Incolab Services Russia S.C.	CERTIFICATE REFERENCE 2410439RUS	ISSUE DATE 31 October 2024
---	-------------------------------------	-------------------------------

Test results

PARAMETER	RESULT	BASIS
Total moisture	6.5 %	As received
Ash	0.3 %	As received
Ash	0.4 %	Dry basis
Volatile matter	79.2 %	As received
Volatile matter	84.7 %	Dry basis
Gross calorific value	4,654 kcal/kg	As received
Gross calorific value	4,977 kcal/kg	Dry basis
Net calorific value (Qv)	4,318 kcal/kg	As received
Sulphur	0.01 %	As received
Sulphur	0.01 %	Dry basis
Bulk density	700 kg/m3	As received
Average length	14.3 mm	Sample
Average diameter	6.0 mm	Sample
Durability	99.6 %	Sample
Dust content (-3.15 mm)	0.2 %	Sample

DOCUMENT STATUS	This is a commercial data summary prepared from Incolab Certificate of Assay Ref. 2410439RUS dated 31 October 2024. It is not the original laboratory certificate. The original certificate is available from SIB PELLET upon request.
-----------------	--

Methods stated in the source certificate include ISO 18134-2, ISO 18122, ISO 18123, ISO 18125, ISO 16994, ISO 17828, ISO 17829, ISO 17831-1 and ISO 5370. Values are sample-specific and do not by themselves constitute ENplus certification.